

Technical Data Sheet

FILM LAMINAR MATE POLIMERICO ATP GL 410 PM BOBINA 50
METROS APTO PARA LAMINAR IMPRESIONES CON TINTAS UV

Product Description:

High quality optically mat polymeric REACH and RoHS compliant PVC for lamination of various print media. Suitable for long term outdoor and indoor light box applications. Particularly suitable for applications requiring very high clarity. Furthermore this laminate can be used to protect UV printed medias.

Product structure:

Support	Soft-PVC-film, 70µm, polymer One side siliconised
Interliner	surface-coated paper, white, 63 g/m ² pure polyacrylic ,
Adhesive	permanent, transparent 0.1 mm 30 g/m ²
Total Thickness	
Adhesive weight	

Characteristics:

		Average Value	Test Method
Adhesion on steel:	(after 24 h)	11 N/25mm	AFERA 5001
Dimensional Stability:	MD	< -3%	FTM 14
Dimensional Stability:	CD	< 1.5%	FTM 14
Gloss Units 85°		~13	DIN EN ISO 2813
Flammability:		B1	DIN 4102

Environmental Performance:**Chemical resistance:****Conditions****Appearance**

24h at room temperature and 4h in propanol 24h at

no change

room temperature and 48h in water

no change

Temperature resistance:**Conditions****Appearance**

24h at room temperature and then 24h at 80°C 24h

no change

at room temperature and then 24h at -40°C

no change

Humidity resistance:**Conditions****Appearance**

24h at room temperature and then 24h at 38°C and 98% humidity

no change

Application temperature:

min. +8°C

End-Use Temperature range:

from -40°C to +90°C

Shelf life:

2 years (see application information)

Durability:

5 years

The estimated durability is based on accelerated ageing tests and refers to a vertical exposure under middle European climates. The durability of the product depends on the substrate's preparation, the atmospheric conditions and the environmental influence. Exposure to extreme conditions (tropical climate, high humidity, high UV-light exposure or polluted areas) can decrease the durability in a dramatically way.

All our products are subjected to a strict quality control by our QM-System. The information is based on our present knowledge and our experience. Because of the large number of possible influences during the processing and application of our products, this information does not release the user from the obligation to conduct his own tests and trials. Users of our products are responsible for observing any patent rights that may exist and for following existing regulations. Our applications technology section is always pleased to give advice about suitability tests on original materials.

